

EO-B-023D

Cat.-No. 6145

MULTI-FLUX Special Flux for wave-, selective-, hand-soldering

WEEE /RoHS-compliant

[OSP-kompatibel] / ISO 9454: 1231 (1.2.3.A)

DIN-EN 61190-1-1 (acc. J-STD004) / IEC : REL0 NO CLEAN

EO-B-023D is an universally suitable for wave-, selective- and hand-soldering of PCBs and complies with specification DIN-EN 61190-1-1: L0

("NO CLEAN"). Accordingly, it contains organic, halogen-free activating additives with resin in a combination specially tuned to the thermal requirements of the soldering processes. EO-B-023C can be applied by brushing, spraying, dipping etc.. The solids content is 6% by weight.

Additional information on the ingredients (hazardous substances), safe handling, storage, transport and disposal can be found in the current safety data sheet (SDS, SDS, MSDS).

This flux is very versatile. There are good results for manual, wave and selective soldering, as well as for cable assembly / wire tinning. The general rule of applying fluxes applied in principle as low as possible also applies to this product.

Instructions for use:

Sprayfluxing: If possible, try at first a quantity of 15 – 25 ml/min. and observe the distribution of the flux. After that, correct the quantity. Air-pressure: 18 – 20 l/min.

Preheating: Entering the solder-wave, the temperature on the topside of the pasteboards should be 80 – 110 °C, dependent on type of boards, lay-out etc. – in case of using lead-free solders, preheating temperatures of 100 – 130 °C on the topsides are possible.



Technical Data

| | |
|---------------------------|--|
| Appearance/smell | light yellow- amber coloured, clear liquid |
| Solids content | 5,8 – 6,2 Gew.-% |
| Density at 20 °C | 0,799 (+/- 0,003) g/ml |
| Acid number | 16 – 18 mg KOH/g |
| Activators | Resin-carboxylic and dicarboxylic acidscomplex |
| Solvents | short chain alcohols |
| Flash point | 12 |
| Storage (recommendation): | Store at 5-25 ° C, dry, sealed |

Application area

Wave-, selective- and manual soldering processes, as well as cable assembly

Packaging units

- | | | |
|---|---|--|
| <input checked="" type="checkbox"/> Canister / 5l and 20l | <input type="checkbox"/> Metering bottle / ml | <input type="checkbox"/> Spray bottle / ml |
| <input type="checkbox"/> Granulate / Size | <input type="checkbox"/> Metering pen / ml | <input type="checkbox"/> Injection / ml |

EMIL OTTO Flux- und Oberflächentechnik GmbH
 D-65346 Eltville – Eltviller Landstr. 22
 Tel.: +49 (0)6123 / 70 46 0 – Fax: +49 (0)6123 / 70 46 15



The information in our descriptions are typical values. They are provided for your information, but do not represent any specifications or assurances of properties in the sense of liability and warranty claims. The same applies to the application-related information; these are non-binding and do not relieve our customers of their own testing of our products for their suitability for the intended purpose, process or purpose.